



Basis Nappa Specifications

Test	Test Method	Measurement Unit	Requirement
Thickness	DIN 53326	mm	1.0 - 1.4
Mass per unit area	DIN 53327	g/qm	620 - 980
Tension test Tensile test Breaking elongation	DIN 53328 Specimen 2 Specimen 2	N %	> 120 35 - 70
Tear strength	DIN 53329/A DIN 53329/B	N	> 25 > 20
Behaviour after 20,000 folds	DIN 53351		No cracks at 6 times magnifying
Behaviour after ageing 1 period 10,000 folds			No cracks at 6 times magnifying
Water vapour permeability	DIN 53333	mg/qcm	1.0
Rub fastness Dry Wet Wet after storage in water	DIN 53339 evaluation DIN 54002	Class Class Class	4 - 5 4 - 5 4 - 5
Sweat		Class	4 - 5
Top coat adhesion		N/cm	3.5
High temperature light exposure	DIN 75202	Class blue scale	5.7
Flammability	FMVSS 302	mm/min	< 100
Odour test	VDA 270 C3	Class	< 3
VDA list			Keeping to the list

What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.5-5.5m². Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.